


ASA poly(acrylonitrile-co-styrene-co-acrylate)

PARAMETER	UNIT	VALUE	REFERENCES
GENERAL			
Common name	-	poly(acrylonitrile-co-styrene-co-acrylate)	
IUPAC name	-	2-propenoic acid, butyl ester, polymer with ethenylbenzene and 2-propenenitrile	
CAS name	-	2-propenoic acid, butyl ester, polymer with ethenylbenzene and 2-propenenitrile	
Acronym	-	ASA	
CAS number	-	9003-54-7; 26299-47-8; 26716-29-0	
HISTORY			
Person to discover	-	Herbig and Salyer; Siebel and Otto	
Date	-	1964; 1965	
Details	-	first patent; refined product	
SYNTHESIS			
Monomer(s) structure	-	$\text{H}_2\text{C}=\text{CHC}\equiv\text{N}$  $\text{H}_2\text{C}=\text{CHCOCH}_3$	
Monomer(s) CAS number(s)	-	107-13-1; 100-42-5; 96-33-3	
Monomer(s) molecular weight(s)	dalton, g/mol, amu	104.15; 53.06; 86.09	
Monomer reactivity ratio		AN/ST=0.25/2	Badawy, S M; Dessouki, A M, J. Appl. Polym. Sci., 84, 268-75, 2002.
Method of synthesis	-	grafting rubber which is dispersed with a styrene acrylonitrile (SAN) phase	
Mass average molecular weight, M_w	dalton, g/mol, amu	60,000-200,000	
Rubber particle size	nm	100-1000	Hossain, M M; Moghbelli, E; Jahnke, E; Boeckmann, P; Guriyanova, S; Sander, R; Minkwitz, R; Sue, H-J, Polymer, 63, 71-81, 2015.
STRUCTURE			
Crystallinity	%	0	
COMMERCIAL POLYMERS			
Some manufacturers	-	BASF; Sabic	
Trade names	-	Luran S; Geloy	
PHYSICAL PROPERTIES			
Density at 20°C	g cm ⁻³	1.06-1.1; 1.18 (15% glass fiber)	
Bulk density at 20°C	g cm ⁻³	0.6	
Refractive index, 20°C	-	1.57-1.677	
Gloss, 60°, Gardner (ASTM D523)	%	93-94	
Odor	-	faint specific	
Melting temperature, DSC	°C	180-200	
Softening point	°C	>85 to >100	
Decomposition temperature	°C	320; 395(TGA onset)	

ASA poly(acrylonitrile-co-styrene-co-acrylate)

PARAMETER	UNIT	VALUE	REFERENCES
Thermal expansion coefficient, -40 to 40°C	°C ⁻¹	0.95-1.2E-4; 0.3E-4	
Thermal conductivity, melt	W m ⁻¹ K ⁻¹	0.16	
Glass transition temperature	°C	103-127; -46.5 to -50.9 (core) and 103.7 to 107.1 (shell)	Tolue, S; Moghbeli, M R; Ghafelebashi, S M, Eur. Polym. J., 45, 714-20, 2009.
Specific heat capacity	J K ⁻¹ kg ⁻¹	1,860-2,000 (melt)	
Long term service temperature	°C	-40 to 75	
Heat deflection temperature at 0.45 MPa	°C	84-106; 115 (15% glass fiber)	
Heat deflection temperature at 1.8 MPa	°C	75-103; 110 (15% glass fiber)	
Vicat temperature VST/A/50	°C	80-104; 115 (15% glass fiber)	
Vicat temperature VST/B/50	°C	82-98	
Dielectric loss factor at 1 kHz	-	0.02-0.05	
Relative permittivity at 100 Hz	-	3.5-3.9	
Relative permittivity at 1 MHz	-	3.2-3.5	
Dissipation factor at 100 Hz	E-4	90-110	
Dissipation factor at 1 MHz	E-4	240-340	
Volume resistivity	ohm-m	1E12	
Surface resistivity	ohm	1E13	
Electric strength K20/P50, d=0.60.8 mm	kV mm ⁻¹	35	
Comparative tracking index	-	600	
Coefficient of friction	-	0.4-0.5	Hossain, M M; Moghbelli, E; Jahnke, E; Boeckmann, P; Guriyanova, S; Sander, R; Minkwitz, R; Sue, H-J, Polymer, 63, 71-81, 2015.
Permeability to nitrogen, 25oC	cm ³ m ⁻² d ⁻¹ day ⁻¹	60-100	
Permeability to oxygen, 25oC	cm ³ m ⁻² d ⁻¹ day ⁻¹	150-560	
Permeability to water vapor, 25oC	g m ⁻² day ⁻¹	30-35	
Contact angle of water, 20oC	degree	93.7-97.0	
MECHANICAL & RHEOLOGICAL PROPERTIES			
Tensile strength	MPa	29-51; 110 (15% glass fiber)	Chang, M C O; Garrett, P D, Antec, 2588-93, 1996.
Tensile modulus	MPa	1,870-2,600; 6,600 (15% glass fiber)	
Tensile stress at yield	MPa	38-56	Chang, M C O; Garrett, P D, Antec, 2588-93, 1996.
Tensile creep modulus, 1000 h, elongation 0.5 max	MPa	1,200-1,650	
Elongation	%	7-37	Chang, M C O; Garrett, P D, Antec, 2588-93, 1996.
Tensile yield strain	%	2.8-4.0; 2.5 (15% glass fiber)	
Tensile yield strength	MPa	55-57	Hossain, M M; Moghbelli, E; Jahnke, E; Boeckmann, P; Guriyanova, S; Sander, R; Minkwitz, R; Sue, H-J, Polymer, 63, 71-81, 2015.
Flexural strength	MPa	56-75	

ASA poly(acrylonitrile-co-styrene-co-acrylate)

PARAMETER	UNIT	VALUE	REFERENCES
Flexural modulus	MPa	1,880-2,570	
Compressive strength	MPa	35-65	
Compressive modulus	MPa	1,600-1,900	Hossain, M M; Moghbelli, E; Jahnke, E; Boeckmann, P; Guriyanova, S; Sander, R; Minkwitz, R; Sue, H-J, Polymer, 63, 71-81, 2015.
Young's modulus	MPa	1,900-2,600	Chang, M C O; Garrett, P D, Antec, 2588-93, 1996.
Charpy impact strength, un-notched, 23°C	kJ m ⁻²	160-270; 28 (15% glass fiber)	
Charpy impact strength, un-notched, -30°C	kJ m ⁻²	70-180; 17 (15% glass fiber)	
Charpy impact strength, notched, 23°C	kJ m ⁻²	10-40; 7 (15% glass fiber)	
Charpy impact strength, notched, -30°C	kJ m ⁻²	3-9; 6 (15% glass fiber)	
Izod impact strength, unnotched, 23°C	J m ⁻¹	260	
Izod impact strength, notched, 23°C	J m ⁻¹	65-210	
Izod impact strength, notched, -30°C	J m ⁻¹	24-35	
Shear modulus	MPa	700-900	
Rockwell hardness	-	R100-103	
Shrinkage	%	0.45 (parallel); 0.9 (normal)	
Melt viscosity, shear rate=1000 s ⁻¹	Pa s	150-200	
Melt volume flow rate (ISO 1133, procedure B), 220°C/10 kg	cm ³ /10 min	4-25	
Melt index, 220°C/10 kg	g/10 min	5.2-15	
Water absorption, equilibrium in water at 23°C	%	0.55-1.65; 1.42 (15% glass fiber)	
Moisture absorption, equilibrium 23°C/50% RH	%	0.15-0.35; 0.3 (15% glass fiber)	
CHEMICAL RESISTANCE			
Acid dilute/concentrated	-	resistant	
Alcohols	-	resistant-fair	
Alkalis	-	resistant	
Aliphatic hydrocarbons	-	resistant	
Aromatic hydrocarbons	-	non-resistant	
Esters	-	non-resistant	
Greases & oils	-	resistant	
Halogenated hydrocarbons	-	non-resistant	
Ketones	-	non-resistant	
Good solvent	-	chloroform, dichlorobenzene, diethyl ether, DMF, ethyl benzoate, ethyl chloride, mesityl oxide, methyl chloride, methyl propyl ketone, xylene	
Non-solvent	-	acetamide, ethylene glycol, glycerin, triethanolamine	

ASA poly(acrylonitrile-co-styrene-co-acrylate)

PARAMETER	UNIT	VALUE	REFERENCES
FLAMMABILITY			
Flammability according to UL-94 standard; thickness 1.6/0.8 mm	class	HB	
Ignition temperature	°C	>400	
Autoignition temperature	°C	>400	
Limiting oxygen index	% O ₂	19	
Char at 500°C	%	1.12	
Volatile products of combustion	-	CO, CO ₂ , cyanides, ammonia, acrylonitrile, styrene, nitrogen	
WEATHER STABILITY			
Tensile strength retention	%	104 (40 months outdoors)	
Erosion rate (exposure for 10 years)	m year ⁻¹	8.8E-10 (Florida) 12.0E-10 (Arizona)	
Stabilizers	-	UV absorbers: 2-(2H-benzotriazol-2-yl)-p-cresol; 2-(2H-benzotriazole-2-yl)-4,6-di-tert-pentylphenol; 2-(2H-benzotriazole-2-yl)-4-(1,1,3,3-tetraethylbutyl)phenol; 2-[4,6-bis(2,4-dimethylphenyl)-1,3,5-triazin-2-yl]-5-(octyloxy)phenol; HAS: 1,3,5-triazine-2,4,6-triamine, N,N''[1,2-ethanediy-bis[[[4,6-bis[butyl(1,2,6,6-pentamethyl-4-piperidiny) amino]-1,3,5-triazine-2-yl]imino]-3,1-propanediy]-bis[N',N''- dibutyl-N',N''-bis(1,2,2,6,6-pentamethyl-4-piperidiny)-; bis(2,2,6,6-tetramethyl-4-piperidyl) sebacate; 2,2,6,6-tetramethyl-4-piperidiny] stearate; 1, 6-hexanediamine, N, N'-bis(2,2,6,6-tetramethyl-4-piperidiny)-, polymers with 2,4-dichloro-6-(4-morpholinyl)-1,3,5-triazine; 1,6-hexanediamine, N,N'-bis(2,2,6,6-tetramethyl-4-piperidiny)-, polymers with morpholine-2,4,6-trichloro-1,3,5-triazine reaction products, methylated; Phenolic antioxidant: phenol, 4-methyl-, reaction products with dicyclopentadiene and isobutene; Screener: carbon black	
BIODEGRADATION			
Stabilizers		silver compound is added to Luran S BX 13042 to impart its surface with germicidal effect	Anon., Plast. Addit. Compounding, Nov/Dec., p. 19, 2008.
TOXICITY			
HMIS: Health, Flammability, Reactivity rating	-	1/1/0	
Carcinogenic effect	-	not listed by ACGIH, NIOSH, NTP	
PROCESSING			
Typical processing methods	-	extrusion, injection molding, thermoforming	
Preprocess drying: temperature/time/residual moisture	oC/h/%	80-90/2-6/0.02-0.04	
Processing temperature	oC	225-280 (injection molding); 200-230 (pipe extrusion); 200-250 (sheet extrusion)	
Processing pressure	MPa	0.3-1 (back); 5-10 (injection)	
Additives used in final products	-	Fillers: carbon black, glass beads; release agents; thermal stabilizers	
Applications	-	exterior cable enclosures, impact modifier for PC, large screen displays, marine applications, mirrors for personal watercraft, pool accessories, profiles, recreational vehicle antennas, sheet outdoor furnishings, ski bindings, skylights, spas	

ASA poly(acrylonitrile-co-styrene-co-acrylate)

PARAMETER	UNIT	VALUE	REFERENCES
Outstanding properties	-	high service temperature, low thermal conductivity, weather resistant	
BLENDS			
Suitable polymers	-	AES, PBT, PC, PET, PMMA, PVC	
ANALYSIS			
FTIR (wavenumber-assignment)	cm ⁻¹ /-	C=O – 1733, C-O-C – 1169, CH ₃ – 1387, 1456	Tomar, N; Maiti, S N, J. Appl. Polym. Sci., 113, 1657-63, 2009.

POLYMER
PART